

ADHESION GODIFLEX TPE -S

Thermoplastic Elastomere

Type TPE-S	Shore A	Density	Pro- cessing	UV- stability	ABS/ASA	ABS/PC	PA6	PA6 GF30	PC	PET	PMMA	PPO	PS	SAN	TPU Ester	PBT
AX40-755 UV	25	1.10	I	very good								+				
AS30-394 UV	33	1.02	I	very good	+/++	+/++	+/++									
AK40-783 UV	35	1.10	I	very good				+								
AR20-188 UV	35	0.89	I	good	++					++				++		++
AR20-659 UV	35	0.91	I	very good						+	+			+	+	++
AC30-521 UV	38	0.97	I	good					++	++	++					
AF30-593 UV	42	1.02	I	very good	+/++	+/++										
AJ30-734 UV	43	1.01	E/I	very good			+	++								
AO40-161 UV	45	1.12	E/I	medium	++	++			++	++		++				
AN50-991	48	1.16	I	medium			+/++									
AM30-574	50	1.00	E/I	medium	++				++		++	++	+			
AH40-432 UV	50	1.08	I	very good			+/++	+/++								
AZ20-367 UV	55	0.89	I	very good	++				++	++	++					
AS40-947 UV	55	1.07	I	good			++	+								
AK50-922 UV	56	1.17	E/I	medium	++				++	++		+	++	++		
AH30-834 UV	58	1.04	I	medium	++											
AS20-353 UV	59	0.93	I	good	++				++	++	++	+		++		
AS30-227 UV	62	1.00	E/I	very good	+/++	++										
AT50-892 UV	62	1.18	E/I	medium	++				++	++			++			
AF40-648	68	1.10	E/I		+											
AT50-312 UV	85	1.17	I	good	+											
AO40-155 UV	85	1.06	I	good			++	++								
AO40-755 UV	61	1.11	E/I	good					++		++		++			

+ = very good
 ++ = good
 E = Extrusion
 I = Injection Moulding