

Examples from our product range

			GODIPLAST PVC-U LI71-41 Injection moulding, glass-clear, high-impact resistant	GODIPLAST PVC-U LB61-75 injection blow moulding, glass-clear, high-impact resistant	GODIPLAST PVC-U LY71-53 Extrusion, high-impact resistant, antistatic	GODIPLAST PVC-U LO71-14 Extrusion, glass-clear, high-impact resistant	GODIPLAST PVC-U LB71-47 Injection moulding, glass-clear, high-impact resistant	GODIPLAST PVC-U LY61-96 Extrusion, high-impact resistant	GODIPLAST PVC-U LF71-73 Extrusion, glass-clear, high-impact resistant	GODIPLAST PVC-U LR 63-06 Blow moulding, glass-clear, high-impact resistant
Density	DIN 53479	g/cm³	1,37	1,31	1,35	1,36	1,36	1,33	1,36	1,34
Elongation at break	DIN EN ISO 527	%	3	2	3	3	3	3	3	3
Tensile strength	DIN EN ISO 527	N/mm²	55	43	57	57	55	50	57	48
Notched impact strength	DIN 53453	kJ/m²	4	12	7	7	4	12	7	30
Vicat softening point	DIN EN ISO 306 B/50	°C	77	69	78	78	78	76	78	75
Heat distortion temperature	DIN EN ISO 75	°C	65	57	66	66	64	64	66	62