

Exemples tires de notre programme de livraison

			GODIPLAST PVC-U LI71-41	GODIPLAST PVC-U LB61-75	GODIPLAST PVC-U LY71-53	GODIPLAST PVC-U LO71-14	GODIPLAST PVC-U LB71-47	GODIPLAST PVC-U LY61-96	GODIPLAST PVC-U LF71-73	GODIPLAST PVC-U LR 63-06
			Injection, translucide, resistance au choc elevee	Injection-Soufflage, translucide, resistance au choc elevee	Extrusion, resistance au choc elevee, formule antistatique	Extrusion, translucide, resistance au choc elevee	Injection, translucide, resistance au choc elevee	Extrusion, resistance au choc	Extrusion, translucide, resistance au choc elevee	Soufflage, translucide, resistance au choc elevee
Densite	DIN 53479	g/cm³	1,37	1,31	1,35	1,36	1,36	1,33	1,36	1,34
Allongement a la rupture	DIN EN ISO 527	%	3	2	3	3	3	3	3	3
Resistance a la traction	DIN EN ISO 527	N/mm²	55	43	57	57	55	50	57	48
Resistance au choc avec entaille	DIN 53453	kJ/m²	4	12	7	7	4	12	7	30
Point Vicat	DIN EN ISO 306 B/50	°C	77	69	78	78	78	76	78	75
Temperature de deformation a la chaleur	DIN EN ISO 75	°C	65	57	66	66	64	64	66	62