

Examples from our product range

			GODIPRENE TPU PB17-83	GODIPRENE TPU PG16-01	GODIPRENE TPU PA17-29	GODIPRENE TPU PR18-24	GODIPRENE TPU PY29-31	GODIPRENE TPU PV49-31	GODIPRENE TPU PB28-77	GODIPRENE TPU PB60-54
			natural, Expansion, very good oil resistance, very good hydrolysis resistance	natural, TPU rubber, soft setting	natural, TPU rubber, good elongation at break, good oil and hydrolysis resistance	natural, TPU rubber, good abrasion, very good oil and hydrolysis resistance	natural, TPU rubber, high tensile strength, very good oil and hydrolysis resistance	TPU standard, ester based, high tensile strength, hardest setting, good chemical and oil resistance	natural, High Flex, good abrasion, good chemical, oil and elongation at break resistance, easy processing	natural, High Flex, good chemical and oil resistance, good tensile strength
Density	DIN 53479	g/cm <sup>3</sup>	0,55 - 0,80	1,13	1,18	1,15	1,17	1,23 (ISO 2781)	1,21	1,22
Hardness (Shore A)	DIN 53505	°	70	57	68	75	85	98 (ISO 868)	75	46 (Shore D)
Elongation at break	DIN 53504	%	650	880	930	460	610	400 (ISO 4649)	1200	570
Tensile strength	DIN 53504	N/mm <sup>2</sup>	7,5	8,1	8,1	14	20	40 (ISO 37)	18,9	60
Abrasion	DIN 53516	mm <sup>3</sup>	80	95	65	45	85	35	24	50