

HAFTVERBUND GODIFLEX TPE -S

Thermoplastisches Elastomer

Type TPE-S	Shore A	Dichte	Ver- arbeitung	UV-Best- ständig- keit	ABS/ASA	ABS/PC	PA6	PA6 GF30	PC	PET	PMMA	PPO	PS	SAN	TPU Ester	PBT
AX40-755 UV	25	1,10	S	sehr gut								+				
AS30-394 UV	33	1,02	S	sehr gut	+/++	+/++	+/++									
AK40-783 UV	35	1,10	S	sehr gut				+								
AR20-188 UV	35	0,89	S	gut	++					++				++		++
AR20-659 UV	35	0,91	S	sehr gut						+	+			+	+	++
AC30-521 UV	38	0,97	S	gut					++	++	++					
AF30-593 UV	42	1,02	S	sehr gut	+/++	+/++										
AJ30-734 UV	43	1,01	E/S	sehr gut			+	++								
AO40-161 UV	45	1,12	E/S	mittel	++	++			++	++		++				
AN50-991	48	1,16	S	mittel			+/++									
AM30-574	50	1,00	E/S	mittel	++				++		++	++	+			
AH40-432 UV	50	1,08	S	sehr gut			+/++	+/++								
AZ20-367 UV	55	0,89	S	sehr gut	++				++	++	++					
AS40-947 UV	55	1,07	S	gut			++	+								
AK50-922 UV	56	1,17	E/S	mittel	++				++	++		+	++	++		
AH30-834 UV	58	1,04	S	mittel	++											
AS20-353 UV	59	0,93	S	gut	++				++	++	++	+		++		
AS30-227 UV	62	1,00	E/S	sehr gut	+/++	++										
AT50-892 UV	62	1,18	E/S	mittel	++				++	++			++			
AF40-648	68	1,10	E/S		+											
AT50-312 UV	85	1,17	S	gut	+											
AO40-155 UV	85	1,06	S	gut			++	++								
AO40-755 UV	61	1,11	E/S	gut					++		++		++			

+ = sehr gut
++ = gut
E = Extrusion
S = Spritzguß