

# ADHÉSION GODIFLEX TPE -S

## Elastomère Thermoplastique

Type TPE-S	Shore A	Densité	Process	Résistance UV	ABS/ASA	ABS/PC	PA6	PA6 GF30	PC	PET	PMMA	PPO	PS	SAN	TPU Ester	PBT
AX40-755 UV	25	1,10	I	très bon								+				
AS30-394 UV	33	1,02	I	très bon	+/++	+/++	+/++									
AK40-783 UV	35	1,10	I	très bon				+								
AR20-188 UV	35	0,89	I	bon	++					++				++		++
AR20-659 UV	35	0,91	I	très bon						+	+			+	+	++
AC30-521 UV	38	0,97	I	bon					++	++	++					
AF30-593 UV	42	1,02	I	très bon	+/++	+/++										
AJ30-734 UV	43	1,01	E/I	très bon			+	++								
AO40-161 UV	45	1,12	E/I	moyen	++	++			++	++		++				
AN50-991	48	1,16	I	moyen			+/++									
AM30-574	50	1,00	E/I	moyen	++				++		++	++	+			
AH40-432 UV	50	1,08	I	très bon			+/++	+/++								
AZ20-367 UV	55	0,89	I	très bon	++				++	++	++					
AS40-947 UV	55	1,07	I	bon			++	+								
AK50-922 UV	56	1,17	E/I	moyen	++				++	++		+	++	++		
AH30-834 UV	58	1,04	I	moyen	++											
AS20-353 UV	59	0,93	I	bon	++				++	++	++	+		++		
AS30-227 UV	62	1,00	E/I	très bon	+/++	++										
AT50-892 UV	62	1,18	E/I	moyen	++				++	++			++			
AF40-648	68	1,10	E/I		+											
AT50-312 UV	85	1,17	I	bon	+											
AO40-155 UV	85	1,06	I	bon			++	++								
AO40-755 UV	61	1,11	E/I	bon					++		++		++			

+ = très bon  
++ = bon  
E = Extrusion  
I = Injection